Epiform Series Insulating Powder Resin for Bus-Bars

Features

Provides excellent flexibility.

 Suitable for bus bars where a large distortion occurs at the time of installation.

	Grade	Features	Curing Condition	Tg	Cupping Test	CTI	UL 94 Flame Resistance
			(℃×min)	(°C)	(mm)	(—)	(—)
	F-450	Balance Type	190 ×15	120	1 or less	300	V-0 Equivalent
Under Developmen	F-460	High Flexibility	190 × 5	100	12	600	
Under Developmen	F-472	Flexibility Flame Resistance	190 × 5	110	10	300	V-O Equivalent

The values above are representative values.

